Finishing

Shoe Upper

CLIENT TFL RECIPE NO. BU 5967

ARTICLE N°10 MAREA BASED ON WE RECIPE NO.

MATERIAL COW SIDE DATE FEB. 2023
COLOUR TPX 18-1015 TECHNICIAN Borgia Roberto

Product	1	2	3	4	5	6	Procedure
RODA®Pure Oil DW 5040	1000				ļ		1) 1X ROLLER 30C - @ 50°C
					i		7 gr. sqft
					i		REST OVER NIGHT
					i		DRY MILL 6 hrs 60°C - 50% UMIDITY
			L	L	i !		DRY MILL 6 hrs 50°C -
							FINAL FELT POLISH
					! :		1
					ļ		
			ļ		¦		
					<u> </u>		
			L		! L	L	
					<u> </u>		
					i		
					 		
			L	L			
					ļ		
					ļ		
					<u> </u>		
					ļ		
					i 		
					i 		
	T T						
					i		
					i		
					ļ		
					i 		
Tatal	1000	•	•	•	_	^	
Total	1000	0	0	0	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

