Finishing

Shoe Upper

CLIENT TFL RECIPE NO. BU 5962

ARTICLE N°11 BROWNIE BASED ON WE RECIPE NO.

MATERIAL F.G. CALF SIDE DATE FEB. 2023
COLOUR TPX 19 - 1518 TECHNICIAN Borgia Roberto

Product	1	2	3	4	5	6	Procedure
RODA®Pure Oil AA 4040	100		! !			 	
WATER	200		i	100		Ť	1) 1X ROLLER 30C
RODA®Oil 1449	·	100	 	i		†	REST OVER NIGHT
RODA®Wax 1423	<u>-</u>	100	 			†	
RODA®Ground UP-XS			80			<u> </u>	2) 1X ROLLER 30C
RODA®Lac WG/4			20	100		1	REST OVER NIGHT - POLISH
RODA®Pure Wax 4039	İ		80			Ī	- T
RODA®Pur WX 1418/F			100				3) 1X ROLLER G25G - 8gr.sqft
RODA®Pur 5101/N			50				REST OVER NIGHT
AQUADERM®Additive GF			5	10			
RODA®Fix 5792/N2				100			4) 2X SPRAY
							IRON 100°C - 50Kg
							PLATE 100°C - 70Kg
							MILLING TO EFFECT
						Ī	
	i					Ī	1
	T I					T	- †
						<u> </u>	
						İ	
				i		T	
	<u>-</u>		!	<u> </u>		İ	
						†	
			İ	ii		†	
			i	ii		†	
	<u>-</u>		! !	†i		†	
Total	300	200	335	310	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

