

# Finishing Shoe Upper



CLIENT **TFL**  
 ARTICLE **N°12 PELTRO**  
 MATERIAL **Half Calf**  
 COLOUR **TPX 16-0806**

RECIPE NO.  
 BASED ON WE RECIPE NO.  
 DATE  
 TECHNICIAN

**MEMA 23020**  
**29 March 2023**  
**Maurizio Menichetti**

Product	1	2	3	4	5	6	Procedure
RODA® Base Reco 12	600						1) 2X SPRAY
WATER	600	400	200	200			IRON 100°C 30 atm
RODA® Lite 07 Mix	30						
RODA® Link 5504/N	6						2) 2-3X SPRAY
RODA® Wax Mono		50					Micro haircell 90°C 30 atm
RODA® Pure Luster 1430		50					+2-3X SPRAY
RODA® Pur EP 19/F		150					
BAYDERM®Bottom 10 UD		70					3) 2X SPRAY
RODA® Pur EP 5		20					
RODA® Lite 07 Mix		45					4) 2X SPRAY
RODA® Fix WF 2185			100	100			SANDBLAST 80°C 30 atm
RODA® Fix 5188/N Gloss			100	100			
RODA® Poliperl Iridescent			4				
RODA® Link PAX			4	4			
AQUADERM® Additive XF				4			
<b>Total</b>	<b>1236</b>	<b>785</b>	<b>408</b>	<b>408</b>	<b>0</b>	<b>0</b>	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.