Finishing

Shoe Upper

CLIENT TFL RECIPE NO. BU 6009

ARTICLE N°13 MANGO BASED ON WE RECIPE NO.

MATERIAL LAMB SKIN DATE APRIL 2023

COLOUR TPX 17 - 1452 TECHNICIAN Silvestro Giaquinto

Product	1	2	3	4	5	6	Procedure
RODA® Lite 07 mix	20	100	ļ		ļ		1) 2X SPRAY
RODA® Base AF-B/N	100		†				PLATE 120°C - 50 atm
WATER	300	600	700			†	
RODA® Pure Luster 1505	20	100	70			Ī	2) 6X SPRAY
RODA® Pure Luster 1430		50				Ī	
RODA®Pur W 1813/N2		100	200				3) 2X SPRAY
RODA®Pur EP 5/N		50	i			Ī	PLATE 120°C - 50 atm
RODA®Cryl NP 86		50					DRY MILL 4 hrs
RODA®Cryl 108/N2		20	10			i	KISS PLATE
RODA®Pur 5329/N conc.			20			Ī	
RODA®Feel Microsil			5			Ī	
RODA®Link Pax	i i		5		i	Ī	
Total	440	1070	1010	0	0	0	
Total	440	10/0	1010	U	U	U	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.