

Finishing Shoe Upper



CLIENT **TFL**
 ARTICLE **N°16 BRETAGNA**
 MATERIAL **Half Calf F.G.**
 COLOUR **TPX 19 - 0415**

RECIPE NO.
 BASED ON WE RECIPE NO.
 DATE
 TECHNICIAN

MEMA 23001
31 January 2023
Maurizio Menichetti

Product	1	2	3	4	5	6	Procedure
RODA® Pur ADX	100		20				Embossed wet
WATER	300	400	450	150			"Barontini" By Stampe e Stampe
I.P.A.	100						DRI MILLING 12h
RODA® Lite 07 Mix		30	50				
RODA® Ground Reco 5		400					1) 1X SPRAY
RODA® Pur WX 1418/F		100					
RODA® Wax 944			70	5			2) 1X SPRAY
EUDERM® Nappa Soft S 2			30				IRON 90°C 30 atm
RODA® Pure Luster 1430			30				
RODA® Cryl NP 87			100				3) 3-4X SPRAY
BAYDERM® Bottom 10 UD			50				
RODA® Fix 5792/N				30			4) 2X SPRAY
RODA® Pur 5329/N Conc				120			IRON 100°C 20 atm
RODA® Pur 5008				15			DRY MILLING 8h
RODA® Link 4009				15			STAKING
AQUADERM® Additive XF				2			
AQUADERM® XL 71				3			
Total	500	930	800	340	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.