Finishing

Shoe Upper

CLIENT TFL RECIPE NO. BU 6008

ARTICLE N°18 KENT BASED ON WE RECIPE NO.

MATERIAL GOAT SKIN DATE APRIL 2023

COLOUR TPX 19 - 1862 TECHNICIAN Silvestro Giaquinto

Product	1	2	3	4	5	6	Procedure
RODA® Lite 07 mix	50				ļ	 	1) 2X SPRAY
SELLA® Derm M2 MIX	10				Ī	Ī	PLATE 120°C - 50 atm
WATER	550	500			†		+ 6X SPRAY
RODA® Pure Luster 1505	100	150					
RODA® Bind TLC 385	50						2) 2X SPRAY
RODA® Pure Luster 232	100	50					PLATE 120°C - 50 atm
RODA®Pur 5427/N	50	100					DRY MILL 4 hrs
RODA®Pur W 1817	50				<u> </u>		KISS PLATE
RODA®Cryl 744	50			Ī	Ĭ	i	
RODA®Cryl 108/N2	25	50					
RODA®Pur 5329/N conc.		150					
RODA®Link Pax		10					
				<u> </u>	1		+ +
					1		+ +
							+ +
					 		
				1	 		
			_	_			
Total	1035	1010	0	0	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.