Finishing



CLIENT TFL RECIPE NO. BU 5993

ARTICLE N°19 SCOTS BASED ON WE RECIPE NO.

MATERIAL Cow Side F.G. DATE MARCH 2023
COLOUR TPX 19-4006 TECHNICIAN GIRAUDO

Product	1	2	3	4	5	6	Procedure
BAYDERM ®Prebottom APV	150		ļ	30		 	1) 1X SPRAY
water	500	430	500		300	200	
I.P.A.	350		! !				2) 3X/4X SPRAY
RODA®Lite 07 mix		100					
EUDERM® X Grade SF		70	Ī				3) 1X SPRAY
RODA®Pure Luster 1505		50					EMBOSS
PRIMAL™ SCL 371		100	<u> </u>				
PRIMAL™ SB 160		50	† !				4) 4X TIPPING ROLLER
AQUADERM®Bottom LT		150	Ī				
МОР		50					5) 2X SPRAY
RODA® Lac WG/4			500				IRON 100°C - 20 Kg
RODA® Bind TLC 385				50	150		
RODA® Fix 5188/N Gloss				300			6) 1X SPRAY
RODA® Silver Top 578 SF				10			KISS PLATE
RODA® Cor HTP MIX			ļ 	10			
AQUADERM®Finish HAT	i		<u> </u>		150	<u> </u>	
RODA®Pur 5329/N conc.			<u> </u>		100		
RODA®Feel Microsil					10		
RODA®Link Pax					15		
RODA®Wax 4053						70	
RODA®Wax KCF 699						20	
RODA®Pur 5427/N						50	
RODA®Wax SCH/N						10	
							
							+ +
			 				
Total	1000	1000	1000	400	725	350	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

