# Finishing
## Leather Goods

| | | | |
|---|---|---|---|
| CLIENT | **TFL** | RECIPE NO. | **BU 5985** |
| ARTICLE | **N°20 FARROW** | BASED ON WE RECIPE NO. | |
| MATERIAL | **COW SIDE BUFFED GRAIN** | DATE | **01 March 2023** |
| COLOUR | **TPX 17-1422** | TECHNICIAN | **BRUNO PARREIRA** |

| Product | 1 | 2 | 3 | 4 | 5 | 6 | Procedure |
|---|---|---|---|---|---|---|---|
| **RODA®Feel CLD-N2** | 200 | | | | | | |
| **Water** | 700 | 700 | 250 | | | | 1) 1X SPRAY |
| **PM 3870** | 100 | | | | | | REST OVER NIGHT |
| **RODA®Pur 8103** | | 300 | | | | | EMBOSS |
| **RODA®Cryl 108/N2** | | | 100 | | | | |
| **RODA®Pur WX 1418/F** | | | 150 | | | | 2) 2X TIPPING ROLLER |
| **RODA®Pure Luster 682** | | | 250 | | | | |
| **RODA®Bind TLC 385** | | | 250 | | | | 3) 4-5X SPRAY |
| **SELLA®Derm M2 Mix** | | | X | | | | IRON 100ºC |
| | | | | | | | REST FEW HRS |
| | | | | | | | DRY MILL TO EFFECT |
| **Total** | **1000** | **1000** | **1000** | **0** | **0** | **0** | |

**Comments:**

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.