Finishing							
Leather Good	S						
CLIENT <b>TFL</b>				RECIPE	NO.		BU 5892
ARTICLE N°25 EDO	BASED ON WE RECIPE NO.						
MATERIAL SHEEP SKIN	DATE MARCH 2023						
COLOUR <b>TPX 17 - 1461</b>	TECHNICIAN BORGIA ROBERTO						
Product	1	2	3	4	5	6	Procedure
RODA <sup>®</sup> Lite 07 MIX	100						1) 2X/3X SPRAY
RODA <sup>®</sup> Base 5514	250						
RODA <sup>®</sup> Base AF-B/N	250		200				2) 1X SPRAY
WATER	300	200	300	300			EMBOSS "CARIBU"
RODA <sup>®</sup> Bind TLC 385	60						
RODA <sup>®</sup> Lac WG/4		100					3) 3X SPRAY
RODA <sup>®</sup> Pur WX 1418/F			40				
RODA <sup>®</sup> Wax SCH/N			80	30			4) 2X SPRAY
AQUADERM®XL71			10				PLATE 100°C - 50 Kg - 1"
SELLA®Derm M2 MIX			2				DRY MILL 6 hrs
RODA <sup>®</sup> Fix 5792/N2				200			
RODA <sup>®</sup> Fix 6271/B				200			
RODA <sup>®</sup> Pur 5008				30			
RODA <sup>®</sup> Link 4009				30			
l – I		i					
l		1					
l		1					
ŀ		<u> </u>					
				1			
		<u> </u>					
		<u> </u>		1			
Total	960	300	632	790	0	0	
Comments:							

5

Einiching

 $\mathsf{RODA}^{\otimes}$  is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.