

# Finishing

## Shoe & Leather Goods



CLIENT **TFL**  
 ARTICLE **N°27 PRESIDENT**  
 MATERIAL **SHEEP SKIN**  
 COLOUR **TPX 16-1255**

RECIPE NO.  
 BASED ON WE RECIPE NO.  
 DATE  
 TECHNICIAN

**BU 5971**  
**MARCH 2023**  
**Borgia Roberto**

Product	1	2	3	4	5	6	Procedure
RODA®Lite 07 MIX	50	30					1) 3X SPRAY
RODA®Wax 2009/N	300						PLATE 110°C - 70 atm
RODA®Pur 5101/N	400	500	400				
WATER	100						2) 3X SPRAY
RODA®Ground UP-XS	100						
RODA®Polipearl Copper	10	10					3) 3X SPRAY
RODA®Pure Luster 1505		100	40				PLATE 120°C - 70 atm
RODA®Pure Luster 682		200	70				REST FEW HRS
RODA®Pur 64/N		150					DRY MILL TO EFFECT
RODA®Pur 5427/N		80	100				
Aquaderm®XL 71		5	5				
RODA®Bind TU 688/B			30				
RODA®Feel Microsil			10				
RODA®Pur 5008			20				
RODA®Link 4009			20				
<b>Total</b>	<b>960</b>	<b>1075</b>	<b>695</b>	<b>0</b>	<b>0</b>	<b>0</b>	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.