Finishing

Leather Goods

CLIENT TFL RECIPE NO. BU 5995

ARTICLE N°4 BRONX BASED ON WE RECIPE NO.

MATERIAL COW SIDE DATE April 2023
COLOUR TPX 19 - 0415 TECHNICIAN Borgia Roberto

Product	1	2	3	4	5	6	Procedure
- Todace	-		,	-	,	Ü	11 occurre
AQUACAST®S	100						BUFFING PAPER 400
RODA®Cor HTP Mix	30						DRY MILL OVER NIGHT
RODA®Bind TLC 327	50						
WATER	300						1) 1X SPRAY
BAYGEN®Compact DD		550					SANDBLAST 90°C - 30Kg
PRIMAL®SB 100		250					
EUDERM®Matt SN 2		50					2) 1X ROLLER 25G
RODA®Lite 07 MIX		150					IRON 90°C - 30Kg
BAYGEN® Top U 01			1000				+ 2X ROLLER 25G
BAYGEN® Hardener SN 2			670				IRON 90°C - 30Kg
Solvent Mix			350				+ 2X ROLLER 25G
							3) 1X CURTAIN COATER - 16/18 gr.sqft
	46.5	40		-	-	_	
Total	480	1000	2020	0	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.