Finishing

Shoe Upper

CLIENT	**TFL**	RECIPE NO.	**BU 6145**
ARTICLE	**N°3 REBECCA**	BASED ON WE RECIPE NO.	
MATERIAL	**Bovine full grain**	DATE	**28 02.2024**
COLOUR	**TPX 19-1322**	TECHNICIAN	**GIRAUDO**

Product	**1**	**2**	**3**	**4**	**5**	**6**	**Procedure**
RODA® Oil 1449	360						
RODA® Wax 1423	180		50				1) 1X ROLLER 30C, 8 gr sq.ft
RODA® Pure Prebase 772	180						REST OVER NIGHT
WATER	180	500	530	550			FELT POLISH
EUDERM® Driver PE-C	100	350					
RODA® Pur ADX		150					2) 1X SPRAY
RODA® Lite 07 MIX			30				
RODA® Pure Luster 1430			100				3) 3X SPRAY
RODA® Bind TLC 385			50	150			
PRIMAL™ FGR			100				4) 2X SPRAY
BAYDERM® Bottom 10 UD			100				IRON 110°C - 50 BAR
RODA® Cryl 108/N2			30				DRY MILL 1H
Sella® Derm M2 MIX			10				KISS PLATE
RODA® Wax KCF 616				20			
RODA® Wax KCF 699				50			
RODA® Pur 5427/N				150			
RODA® Fix 5100/N				50			
RODA® Link Pax				25			
RODA® Feel S 2075				5			
Total	**1000**	**1000**	**1000**	**1000**	**0**	**0**	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.