## Finishing Shoe Upper



CLIENT TFL								BU 6203
ARTICLE N°1 TAURUS						ON WE	RECIPE	
MATERIAL COW SIDE BUFFED GRAIN					DATE			20 February 2024
COLOUR <b>TPX 19-1314</b>					TECHN	ICIAN		BRUNO PARREIRA
Product		1	2	3	4	5	6	Procedure
RODA <sup>®</sup> Pur ADX		200						
WATER		400	350	350	360			1) 1X SPRAY
RODA <sup>®</sup> Pentrator IE 880/N2		400	100	100				
RODA <sup>®</sup> Ground UP-XS			400					2) 3X SPRAY
RODA <sup>®</sup> Pur WX 1418/F			150					IRON 100ºC
RODA®Wax 4097/N				50				
RODA <sup>®</sup> Bind 682				100				3) 4X SPRAY
RODA <sup>®</sup> Pure Luster 1505				100				
RODA <sup>®</sup> Cryl NP 87				50				4) 3X SPRAY
, RODA <sup>®</sup> Cryl 108/N2				70				IRON 110ºC
RODA <sup>®</sup> Pur 5302/N				100				DRY MILL 4 H
RODA <sup>®</sup> Pur 5427/N				80				
AQUADERM® XL71				10	25			
SELLA <sup>®</sup> Derm M2 MIX				Х				
RODA <sup>®</sup> Bind TLC 385					150			
RODA <sup>®</sup> Pur 5805/N3					450			
RODA <sup>®</sup> Feel Microsil					15			
Total 1000 1000 1010			1010	1000	0	0		
Comments:								

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.