

Finishing Garment



CLIENT **TFL**
 ARTICLE **N°13 HARBOUR**
 MATERIAL **GOAT SKIN**
 COLOUR **TPX 18-3817**

RECIPE NO. **ACI24091**
 BASED ON WE RECIPE NO. **ACI24059WE**
 DATE **21 February 2024**
 TECHNICIAN **SANKARALINGAM**

Product	1	2	3	4	5	6	Procedure
RODA® Wax MONO	50	50					CRUST MILLING - 2hrs
RODA® Pure Luster 1430	50	75					1) 3 X SPRAY
RODA® Pur WX 1418/F	50	50					SATILUX - 120°C - 50Kg
RODA® Pure Prebase 678	200						
RODA® Cor HTP Mix	50	50					2) 4 X SPRAY
WATER	600	600	500				IRON 90°C - 20Kg
RODA® Pure Luster 1505		50	100				+ 3 X SPRAY
RODA® Pur 5329/N Conc.		50	100				
RODA® Cryl NP 87		50					3) 2 X SPRAY
RODA® Fix 5090			300				IRON 100°C - 20Kg
RODA® Link PAX			20				MILLING - 1hr
RODA® Feel Microsil			10				
RODA® Feel N4			10				
Total	1000	975	1040	0	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.