Finishing

Shoe Upper

CLIENT TFL RECIPE NO. BU 6140

ARTICLE N°14 DETECTIVE BASED ON WE RECIPE NO.

MATERIAL SHEEP SKIN DATE Feb. 2024
COLOUR TPX 15-4305 TECHNICIAN Borgia Roberto

Product	1	2	3	4	5	6	Procedure
RODA® Lite 07 MIX	100		i 				
RODA® Base 5749	200		L			İ	1) 2X SPRAY
RODA® Base AF-B/N	200		<u> </u>			i	
WATER	400	200	<u> </u>			1	2) 1X SPRAY
RODA® Lac WG/4		100				İ	EMBOSS
RODA® Fix 5188/N Gloss			300				
RODA® Pur ADX			30			i	3) 3X/4X TIPPING ROLLER 48L
RODA® Pure Luster 1505			50	50			· · · · · · · · · · · · · · · · · · ·
RODA® Polipearl MIX			10				4) 2X ROLLER 30C
SELLA® Derm M2 MIX			5			Ī	APPLY "SUPERLUCIDO" 120°C - 50Kg
RODA® Pur WX 1418/F	<u> </u>			100		Ī	REST OVER NIGHT
RODA® Pur 5427/N				230			
RODA® Wax KCF 699				50			
PRIMAL™ SCL 371				60			
RODA® Link PAX				15			
RODA® Pur 5008	Ī			20			
RODA® Link 4009	Ī			20		Ī	
AQUADERM® Fluid H				5			
	Ī						
	i i		[Ţ	
	Ī		i !	i			
						<u> </u>	
	600	262	20-	FF.		•	
Total	900	300	395	550	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

