

# Finishing Leather Goods



CLIENT **TFL**  
 ARTICLE **N°17 AMULETO**  
 MATERIAL **GOAT SKIN**  
 COLOUR **TPX 18-1612**

RECIPE NO. **BU 6202**  
 BASED ON WE RECIPE NO.  
 DATE **MARCH 24**  
 TECHNICIAN **TIRELLI**

Product	1	2	3	4	5	6	Procedure
RODA® Wax 4053	100						
WATER	300	600	500				1) 4X SPRAY
RODA® Lite 07 MIX	40						ROTOPRESS 100°C- 40 ATM
PRIMAL™ FGR		50					DRY MILL 1 H
PRIMAL™ HPB 980		10					
RODA® Pur EP 19/F		40					2) 2X SPRAY
AQUADERM® Bottom LT		80					
RODA® Wax KCF 616		60					3) 2X SPRAY
RODA® Wax MONO		20					ROTOPRESS 120°C- 40 ATM
RODA® Polipearl IRIDE RED		15					DRY MILL 2 H
RODA® Fix 5188/N Gloss			400				
AQUADERM® Finish HAT			100				
AQUADERM® Additive XF			10				
RODA® Feel N4			5				
RODA® Link PAX			40				
<b>Total</b>	<b>440</b>	<b>875</b>	<b>1055</b>	<b>0</b>	<b>0</b>	<b>0</b>	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.