

Finishing

Shoe Upper



CLIENT **TFL**
 ARTICLE **N°21 CASUAL**
 MATERIAL **Cow Side**
 COLOUR **TPX 18-0935**

RECIPE NO.
 BASED ON WE RECIPE NO.
 DATE
 TECHNICIAN

MEMA 24016
09 February 2024
Maurizio Menichetti

Product	1	2	3	4	5	6	Procedure
RODA® Pure Feel CLD	100						1) 2X SPRAY
Water	300	900	500				SANDBLAST 100°C - 30 atm DRY MILLING 5-6hrs
RODA® Base Reco 3		600					
RODA® Lite 07 Mix		60					2) 3X SPRAY
EUDETM® Nappa Soft S2		40					EMBOSS (LOIRA STAMPE & STAMPE)
RODA® Pur WX 1418/F		40					2-3X SPRAY
RODA® Link PAX		9	8				
RODA® Fix WF 2185			400				3) 2X SPRAY Rotopress 70°C - 30 atm
RODA® Lac WR			100				DRY MILLING TO EFFECT
RODA® Feel Microsil			5				
Total	400	1649	1013	0	0	0	

Comments:
 * Mix well together

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.
 Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.
 We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.