

Finishing Shoe Upper



CLIENT **TFL**
 ARTICLE **N° 23 PALESTRA**
 MATERIAL **SHEEP SKIN**
 COLOUR **TPX 18-1550**

RECIPE NO. **BU 6139**
 BASED ON WE RECIPE NO.
 DATE **Feb. 2024**
 TECHNICIAN **Borgia Roberto**

Product	1	2	3	4	5	6	Procedure
RODA® Pure Oil AA 4040	100						1) 2X SPRAY
RODA® Lite 07 MIX	50						
RODA® Pur 5101/N	450						2) 2X SPRAY
SELLA® Derm M2 MIX		20					HAIRCELL 50°C - 90°C
RODA® Pure Luster 1505		70	70	20			KISS PLATE 90°C
RODA® Pure Luster 1430		50	50				
Acqua	350	400	400	200			3) 2X SPRAY
RODA® Penetrator IE 880/N2	50						
RODA® Pur WX 1418/F		70					4) 2X SPRAY
RODA® Cryl 577/N2		100	50				IRON 120°C - 50 Kg
RODA® Pur W 1813/N2		30	100	150			
RODA® Ground UP-XS		30					
AQUADERM® XL 71		10	10				
RODA® Link PAX				3			
RODA® Bind 682				40			
RODA® Wax KCF 699				50			
RODA® Link 4009			20	20			
RODA® Pur 5008			20	20			
Total	1000	780	720	503	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.