Finishing

Leather Goods

CLIENT TFL RECIPE NO. BU 6130

ARTICLE N° 25 LAPPONIA BASED ON WE RECIPE NO.

MATERIAL Cow side F.G. DATE 18.01.2024
COLOUR TPX 18-1030 TECHNICIAN GIRAUDO

Product	1	2	3	4	5	6	Procedure
RODA® Lite 07 Pigment mix	50	50					1) 2X SPRAY
Euderm® X Grade SF	100						
WATER	520	450	600		200		2) 1X SPRAY Ironing
Primal™ FGR	150	100					IRON 100°C @ 50 bar
RODA® Cryl 108/N2	30						+ 2X SPRAY
BAYDERM® Bottom 10 UD	100						
RODA® Poliperl Micro Gold	5	5	2				3) 2X SPRAY
RODA® Poliperl Micro Bronze	5	5	2	5			EMBOSS "NICKEL + SKYLINE"
Euderm® Nappa Soft S 2		100					
RODA® Pure Luster 1430		30					4) 3X/4X TIPPING ROLLER 48L
RODA® Wax KCF 616		50	20				
Primal™ SCL 371		150					5) 2X SPRAY
RODA® Pur 64/N		100					IRON 120°C - 50 Kg
Aquaderm® XL 71		10					
RODA® Pur 5427/N			150	300	200		
RODA® Pure Luster 1505			150				
RODA® Feel KTA 950			5				
RODA® Link PAX			5		5		
RODA® Pur ADX				30			
RODA® Pure Luster 682				50	50		
Total	960	1050	934	385	455	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

