

Finishing Leather Goods



CLIENT TFL
 ARTICLE N°27 PULSAR
 MATERIAL Half Calf
 COLOUR TPX 19-4241

RECIPE NO.
 BASED ON WE RECIPE NO.
 DATE
 TECHNICIAN

MEMA 24014
 07 February 2024
 Maurizio Menichetti

Product	1	2	3	4	5	6	Procedure
RODA® Wax 1423	100						BUFFING 400 PAPER X2
RODA® Wax KCF 684	100						
Water	200		1000	750			1) 1X ROLLER 30C About 8gr.sft. SANDBLAST 120°C
RODA® Pur ADX		100	50				EMBOSS (THEK NEGATIVO, Stampe&Stampe)
IPA		400					2) 1X SPRAY
RODA® Base Reco 3			500				
RODA® Lite 07 Mix			60				3) 4X SPRAY
RODA® Car Dull 92/N			50				
RODA® Fix SFD				500			4) 2-3X SPRAY
RODA® Link PAX				25			5) 3-4X TIPPING ROLLER
Aquaderm®Fluid H				10			
RODA® Fix 5188/N Gloss					300		
RODA® Bind TLC 385					50		
RODA® Cor HTP Mix					10		
RODA® Poliperl Mix					x		
Total	400	500	1660	1285	360	0	

Comments:
 * Mix well together

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.
 Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.
 We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.