## Finishing Leather Goods



| CLIENT <b>TFL</b>                     |                 |      |     |                                | RECIPE                 |      |     | MEMA 24003                     |                       |
|---------------------------------------|-----------------|------|-----|--------------------------------|------------------------|------|-----|--------------------------------|-----------------------|
| ARTICLE N°5 BRUSH BROWN               |                 |      |     |                                | BASED ON WE RECIPE NO. |      |     |                                |                       |
| MATERIAL Half Calf                    |                 |      |     |                                | DATE                   |      |     | 30 January 2024                |                       |
| COLOUR <b>TPX 18-1140 TPX 19-1322</b> |                 |      |     | TECHNICIAN Maurizio Menichetti |                        |      |     |                                |                       |
| Product                               |                 | 1    | 2   | 3                              | 4                      | 5    | 6   | Procedure                      |                       |
| RODA® Penetr                          | rator IE 880/N2 | 150  |     |                                |                        |      |     | Buffed 2X with 400 pap         | ber                   |
| Water                                 |                 | 630  |     |                                | 500                    | 400  | 280 |                                |                       |
| EUDERM <sup>®</sup> Prebottom VE-N    |                 | 150  |     |                                |                        |      |     | 1) 1X Roller 20B about         | 30g/Sf                |
| PRIMAL™ FGR                           |                 | 150  |     |                                |                        |      |     | Rest over night                |                       |
|                                       |                 |      |     |                                |                        |      |     | Vacuum 70°C - 2'               |                       |
| RODA <sup>®</sup> Base WH 0303/N      |                 |      | 500 |                                |                        |      |     | Buffed with 400 paper          |                       |
| RODA® Lite 07 Mix                     |                 |      | 100 |                                |                        | 100  |     |                                |                       |
|                                       |                 |      |     |                                |                        |      |     | 2) 2X Roller 25G               |                       |
| RODA <sup>®</sup> Lac 1028            |                 |      |     | 200                            |                        |      |     | Sandblast roto 90°C 30 atm     |                       |
| RODA <sup>®</sup> Poliperl Micro Gold |                 |      |     | 20                             |                        |      |     | 2X Roller coater 25G           |                       |
| RODA <sup>®</sup> Fix 501             | 10 Gloss        |      |     |                                | 500                    |      |     | RODA <sup>®</sup> Lac 103 Dull | 100                   |
|                                       |                 |      |     |                                |                        |      |     | RODA <sup>®</sup> Lac WR       | 100                   |
| RODA <sup>®</sup> Lac W 4076 Dull     |                 |      |     |                                |                        | 400  |     | Water                          | 400                   |
| RODA <sup>®</sup> Wax KCF 616         |                 |      |     |                                |                        | 100  |     | 1X Spray                       |                       |
|                                       |                 |      |     |                                |                        |      |     | Emboss "Riga media +           | Cork" Stampe e Stampe |
| RODA <sup>®</sup> Fix 5188/N Gloss    |                 |      |     |                                |                        |      | 120 |                                |                       |
| RODA <sup>®</sup> Pur 5329/N Conc     |                 |      |     |                                |                        |      | 40  | 3) Tipping by roller "Ro       | spo" By Colibrì       |
| RODA® Feel M                          | licrosil        |      |     |                                |                        |      | 60  |                                |                       |
| RODA <sup>®</sup> Pure L              | uster 1505      |      |     |                                |                        |      | 60  | 4) 1X Spray                    |                       |
| RODA® Link PAX                        |                 |      |     |                                |                        |      | 5   |                                |                       |
|                                       |                 |      |     |                                |                        |      |     | 5) 1X Spray                    |                       |
|                                       |                 |      |     |                                |                        |      |     | Wipe off with Metoxypropanol   |                       |
|                                       |                 |      |     |                                |                        |      |     | 6) 2X Spray                    |                       |
|                                       |                 |      |     |                                |                        |      |     | Carteggio 120°C 25 atm         |                       |
|                                       |                 |      |     |                                |                        |      |     |                                | I<br>                 |
|                                       |                 |      |     |                                |                        |      |     |                                |                       |
|                                       |                 |      |     |                                |                        |      |     |                                |                       |
|                                       |                 |      |     |                                |                        |      |     |                                |                       |
|                                       |                 | 1    |     |                                |                        |      |     | <u> </u>                       |                       |
|                                       |                 |      |     |                                |                        |      |     |                                |                       |
|                                       |                 |      |     |                                |                        |      |     |                                |                       |
|                                       |                 |      |     |                                |                        |      |     |                                |                       |
|                                       |                 | 1080 | 600 | 220                            | 1000                   | 1000 | 565 |                                |                       |

Comments:

\* Mix well together

RODA<sup>®</sup> is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.