Wet End - Process Formulation (RETAN)



N°16 PALOMAR WET	END.xlsx	Date:	15-Jan-2024
		Technician:	ARBA team
Company:	TFL		
Type of Leather:	Shoe Upper & Leather Goods	Trial - N°:	
Aim of Trial:		Color:	TPX 19-3022
		Piece count:	
Project - N°:	16 PALOMAR	Substance:	1,0-1,2
Material:	1/2 bovine WB ISPARTA	Weight:	
% refer to:	shaved weight	Drum - N°:	

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		300		water	35			
		0,5		CORIPOL® FCT				
drain		0,5		NOVAGAN DC		40	3,5	
drain		300		water	25	10		
		150		water	35			
		1		SELLATAN® CF New.		30		
		5		TANKROM® AB				
		2		BLANCOROL® RCB				
		2		SELLASOL® MI				
		1		CORIPOL® SG		120		
				morning PH=4 drain				
		150		water	35			
		1,5		TANIGAN® PAK				
		1,5	1	Sodium formate		30	4,6	
		0,8	1	Sodium bicarbonate		30	5,7	
drain		4	1	BAYTIGAN® AR		45	5,8	
aram		300		water	25	10	0,0	
		80		water	30	10		
		0,5		CORIPOL® SG	30			
		0,5	1	CORIPOL® ICL				
		4		RETINGAN® R12				
		3		SELLASOL® MI				
				RETINGAN® RLF				
		4	1					
		2		TANIGAN® PR				
		2	-	BAYKANOL® TF2N				
		1,5		SELLA®Fast Bordeaux A				
		0,5		SELLA®Fast Navy A		60		section control
		4		MAGNOPAL® RHN		30		
		4		LEVOTAN® LS				
		4		CORIPOL® VSE				
		4		CORIPOL® SLG		60		
add water		150		water	50	10		
		0,8		Formic acid		5		
		0,8		Formic acid		5		
		1,1		Formic acid		30	3,6	
		2		Formic acid		15		
drain wash		300		water	25	10		
			1					
			1					
						-		
			1					
			+			-		
			L		•			

Mechanical Operation: Proces	ss Information:
vacuum dry 60" a 45°C	
Runni	ng Time:

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer fr om performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the mat erial on receipt. Seller makes no warranty of merchantability or fitness for practical use or application..