Wet End - Pro	ocess Formulation (RETAN)		TFL
N°2 ZIMMER.xlsx		Date:	15-Feb-2024
		Technician:	ROMANO GIUSEPPE
Company:	TFL		
Type of Leather:	Garment Leather	Trial - N°:	2
Aim of Trial:	N°2 ZIMMER	Color:	TPX 19-1338
		Piece count:	25
Project - N°:		Substance:	0,4-0,5
Material:	LAMB SOUTH AFRICA	Weight:	
% refer to:	DRY WEIGHT	Drum - N°:	

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		1.000,00		water	50			
		3,00		SELLASOL® NG liq			45	DRAIN-WASH
		300,00		water	40			
		1,00		ammonia				
		2,00		INVADERM® LU			10	
		7,00		SELLA® Fast Red A				
		1,00		SELLA® Fast Red RTN				
		1,00		SELLA® Fast Red E			30	
		400,00		water	60			
		6,00		CORIPOL® EF-N				
		3,00		CORIPOL® SFC NEW				
		6,00		MAGNOPAL® IPF			60	
		3,00		MAGNOPAL® RHN				
		3,00		MAGNOPAL® PGN			30	
		11,00		formic acid 85%		3X	10+60	
		600,00		water	50			
		3,00		CORIPOL® GLH			30	
		2,00		SELLA® Fast Red A				
		0,20		SELLA® Fast Red RTN				
		0,20		SELLA® Fast Red E			20	
		3,00		formic acid 85%			30	DRAIN -WASH
		600,00		water	50			
		0,50		formic acid 85%			5	
		5,00		CORIPOL® K			30	DRAIN -WASH
	_							
	_							
						<u> </u>		
lechanical Operation:			Process Information:					
ORSE UP OV		F,HANG TO I	DRY					
					Runn	ing Time:		4 hrs 50 m
					1	5		
heir intended purpo lucts subject to gene	ses. Applicatio ral terms of sa	n of the products li le and delivery.	es outside the scope	dge. They do not, however, exempt the custo of our control and therefore comes within th ot released from his obligation to examine the	e customer's sphere of	responsibility. V	Ve guarantee t	he satisfactory quality of our