Wet End -	Process	Formulation	(RETAN))
-----------	----------------	-------------	---------	---

		_
/	4	
_	_	
- N		

N°24 ANDORRA.xlsx		Date:	February 24
		Technician:	
Company:	TFL		
Type of Leather:		Trial - N°:	
Aim of Trial:		Color:	
		Piece count:	
Project - N°:		Substance:	
Material:	W.W. SPLIT	Weight:	
% refer to:		Drum - N°:	•

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		400,00	-	water	40	,		
		1,00		BORRON® SAF		4		
		2,00		CORIPOL® SG			60	
DRAIN		-						
		200,00		water	30			
		10,00		TANIGAN® MB-O LIQ.		3		
		5,00		LEVOTAN® AT-01		4		
		3,00		SELLASOL® TN/FF LIQ.			60	
		100,00		water	50		5	
		4,00		MAGNOPAL® SOF				
		4,00		LEVOTAN®AT-01		4	20	
		10,00		CORIPOL® WK-N				
		2,00		LEVOTAN® WS			40	
		1,00		Formic acid		10	20	
		1,00		Formic acid		10	20	
		1,00		Formic acid		10	20	
DRAIN		1,00						
		300,00		water	55		10	
		1,00		Formic acid		10	10	
		4,00		INVADERM® SN			10	
		X		DILUTED DYESTUFF			5	
		2,00		formic acid			20	
		2,00		SELLA® FIX HPF CONC.			30	
DRAIN		2,00		GEEEN TIXTII I GOIGE.			- 00	
DIVIII		200,00		water	40			
		5,00		CORIPOL® SFC	70		20	
DRAIN		3,00		COMI OL GI O			20	
DIVAIIV								
						-		
Machaniasia	novoti s u s				D	ss Informa	l tion:	
Mechanical O	veration:				Proce	ss intorma	tuon:	
					_	ina Tima.		E has EO asia

Running Time: 5 hrs 50 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our

products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application..