Wet End - Process Formulation (RETAN)



N°29 ZELANDA.xlsx		Date:	
		Technician:	
Company:	<u>TFL</u>	Score:	Select Score
Type of Leather:	Shoe Upper & Leather Goods	Trial - N°:	
Aim of Trial:	ZELANDA	Color:	
		Piece count:	
Project - N°:		Substance:	1,20 mm
Material:	WET-BLUE	Weight:	
% refer to:	Shaved	Drum - N°:	

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		200,00		water	35			
		0,50		BORRON® SAF				
		0,50		Formic Acid		10	40	pH:
Drain								
		100,00		water	35			
		4,00		TANNESCO® HN Liq				
		4,00		TANIGAN® PURE T-A			120	pH:3,8/4,0
	+	4,00		SELLASOL® NG liq				
		2,00		Sodium formate			30	
		0,80		Sodium bicarbonate			30	
		4,00		LEVOTAN® L				
	+	2,00		MAGNOPAL® DP		3	90	pH; 5,0/5,5
Drain								
		200,00		water	30		10	
Drain								
		50,00		water	30			
		2,00		BAYKANOL® TF-2N CO1			10	
	+	2,00		SELLA® Fast dystuffs		10	30	
	+	3,00		LEUKOTAN® 1093		3		
		6,00		MAGNOPAL® PGN				
		6,00		LEVOTAN® L			30	
	+	10,00		TANIGAN® FA-O				
		4,00		Tara				
		4,00		RETINGAN® Pure RS			30	
	+	2,00		TANIGAN® PR				
		2,00		SELLA® Fast dystuffs		10	90	
	+	100,00		water	50		10	
		8,00		CORIPOL® WK-N				
	+	4,00		LEVOTAN® L				
		2,00		LEVOTAN® WS		4	60	
	+	0,80		Formic acid		10	20	II.
	+	0,80		Formic acid		10	20	
	+	0,80		Formic acid		10	20	pH: 3,4/3,6
Drain								
		200,00		water	30		10	
Drain								
		150,00		water	30			
		2,00		CORIPOL® SFC		4	20	
	+							
Mechanical Opera	ation:				Process I	nformatio	n:	
						Running Time: 11 hrs 10 min		
					Running			

| Running Time: 11 hrs 10 m

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application.