



Wet End - Process Formulation (RETAN)

N°4 MOKKA WET END TANNAGE.xlsx

Date: 22-Jan-2024
Technician:

Company:	TFL	Trial - N°:	
Type of Leather:		Color:	18-1140
Aim of Trial:	tannage cropons Tanigan Pure T-A	Piece count:	
Project - N°:	4 MOKKA	Substance:	
Material:	croupon pickel	Weight:	
% refer to:	pelt weight splitted at 5 mm	Drum - N°:	

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		50,00		water	20°C			
		0,10		formic acid				
		6,00		salt			10	Bè: 7-8
				leather into			30	
		5,00		TANIGAN® RFS liq.				
		0,50		sodium formate				
		0,30		sodium bicarbonate			180	pH: 4
		1,00		CORIPOL® SLG				
		20,00		TANIGAN® PURE T-A				
		10,00		mimosa ME				
		10,00		TANIGAN® MBO liq.				
		2,00		SELLATAN® TN			14 ore	automatic night
morning								
		100,00		water	38°C			
		0,50		TANIGAN® BL				
		0,20		oxalic acid			10	
				press / shave				drain

Mechanical Operation:

Process Information:

Running Time: 3 hrs 50 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery. Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application..