Wet End - Process Formulation (RETAN)



N°7 BLACK KNIFE WET END.xlsx

N°7 BLACK KNIFE WET END.xlsx		Date:	25-Jan-2024	
		Technician:	Zampinetti	
Company:	TFL			
Type of Leather:	Shoe Upper & Leather Goods	Trial - N°:		
Aim of Trial:	FASHION 25-26	Color:	TPX 19-1101	
		Piece count:	2 1/2 NBT	
Project - N°:	N° 7 BLACK KNIFE	Substance:	1,1-1,2	
Material:	USA	Weight:	4,800 kg	
% refer to:	shaved	Drum - N°:		

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		200,00		Water	40			
		0,30		Formic acid				
		0,30		BORRON® DNC			60	pH=3,3
Drain - wash								
		150,00		Water	35			
		1,00		CORIPOL® SLG				
		2,00		SELLATAN® AR liq			10	
		3,00		Chrome			60	
		2,00		Sodium formate			30	pH= 3,8
		1,20		Sodium bicarbonate			60	pH=5,3
		3,00		RETINGAN® R7			60	
AUTOMATIC O/N								
				IN THE MORNING			5	pH=5,2
Drain - wash								• •
		30,00		Water	20			
	+	5,00		BAYTIGAN® AR	-	1	30	
	+	0,50		INVADERM® LU	1	1		
		0,50		Ammonia			5	
		2,00		SELLASOL® TN-FF liq				
		3,00		SELLA® FAST BLACK HM conc			60	
		6,00		Tara			00	
		10,00		TANIGAN® MBO liq			60	
		150,00		Water	55		00	
		3,00		CORIPOL® SLG	00			
		3,50		CORIPOL® DX-1202				
		0,50		Sorbitolo			60	
		1,00		Formic acid			20	
		1,50		Formic acid			40	pH=3,7
Drain - wash		1,50					40	p11=0,7
Dialiti - wasit		200,00		Water	50			
		1,00		SELLA® FAST BLACK HM conc	50			
		0,50		SELLA® FAST BLACK HM CONC SELLA® FAST BLACK BR			10	
				Formic acid			10 20	
	+ +	1,00 0,70		SELLA® FAST BLACK HM conc				
	+ +						10	
Droin week	+ +	0,50		Formic acid			20	
Drain - wash	+ +							
	+ +							
	+ $+$							
	+							
	+							
	+ +							
•• • • • • •					_			
Mechanical Opera	ation:	V/			Proce	ess Informa	ation:	
SET OUT - VACU	UM DR	Y						
					-	···· ··		401 00 1
					Runn	ing Time:		10 hrs 20 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer fr om performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes w ithin the customer's sphere of responsibility. We guarantee the satisfactory quality

of our products subject to general terms of sale and delivery. Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the mat erial on receipt. Seller makes no warranty of merchantability or fitness for practical use or application.