

Wet-End



ARTICLE	FOC TANNING	CLIENT	Self
MATERIAL	GOAT PICKLE (Pickle wt*120%)	RECIPE NO.	
QUANTITY	pieces	DATE	Nov 2023
% based on weight:	pickle weight kg	COLOUR	
		TECHNICIAN	B.G

Process	%	kg	Product	Time	Comments
RE PICKEL	100,0		Water		
	6,0		Salt		
	0,5		Sodium Formate	10'	Be-6-7
			add Pickle	10'	
	0,3		Sulphuric Acid (1:20)	10'+10'+30'	pH-3.0, Drain 50% Float
TANNING	1,0		CORIPOL® GLH	10'	
	4,0		SELLATAN® G50-I	90'	
	0,1		Preservative	60'	Check , Penetration
BASIFICATION	0,5		Sodium Formate	40'	
	0,5		Sodium Bi Carbonate	10'+45'	pH- 3.6
	3,0		SELLATAN® RL LIQ	30'	
	0,5		CORIPOL® GLH		
	0,5		CORIPOL® SG		
	0,05		Preservative	60'	
	0,3		Sodium Bi Carbonate	10'X3+120'	pH-3.8-4.0, Darin pile up

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, MAGNOPAL®, SELLA®, SELLASET®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.