

Wet-End



ARTICLE	FOC NAPPA	CLIENT	Self
MATERIAL	GOAT WET WHITE	RECIPE NO.	
QUANTITY	pieces	DATE	Nov 2023
% based on weight:	shaved weight	COLOUR	Brown
	kg	TECHNICIAN	B.G

Process	%	kg	Product	Time	Comments
WET-BACK	200,0		Water		
	0,5		BORRON® SAF		
	1,0		CORIPOL® GLH	60'	Drain/Wash 20'
PRETANNING	100,0		Water		
	3,0		Salt	10'	
	0,6		Sulphuric Acid(1:10)	10'+30'	Check pH - 3.2, Drain %0% Float
	2,0		SELLATAN® G50-I		
	1,0		CORIPOL® GLH	90'	
	0,5		Sodium Formate	20'	
	0,5		Sodium Bicarbonate	30'	check pH - 4.0-4.2
	3,0		SELLATAN® RL LIQ	60'	
	50,0		Water	10'	Keep Over Night
Neutralization			Next Day Run for	20'	
	100,0		Water		
	2,0		SELLASOL® NG LIQ	20'	
	1,0		Sodium Formate	20'	
	1,0		Sodium Bicarbonate		
	1,0		CORIPOL® AT	45'	Check pH - 5.4/5.6 Drain/Wash 20'
RETANNING & DYEIN	50,0		Water		
	2,0		CORIPOL® SLG-I		
	2,0		LEVOTAN® LB		
	2,0		CORIPOL® AT	60'	
	4,0		SELLATAN® RL LIQ	20'	
	4,0		TANIGAN® LM LIQ	20'	
	3,0		MIROSAN® EM		
	3,0		TANIGAN® VT		
	2,0		CORIPOL® SG	20'	
	2,0		BAYKANOL® RT		
	2,0		SELLA® FAST BROWN CR		
	0,5		SELLA® FAST BLACK QX	90'	Check Penetration
FIXING	2,5		Formic Acid	10'+ 10'+ 30'	Drain/Wash 5'

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, MAGNOPAL®, SELLA®, SELLASET®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.