Finishing



CLIENTIILF 24RECIPE NO.IILF2402ARTICLEALBINOBASED ON WE RECIPE NO.ACI23494WEMATERIALSHEEP FGDATE27 December 2023

COLOUR PRISM PINK (TPX 14-2311) TECHNICIAN JOSEPH

Product	1	2	3	4	5	6	7	Procedure
RODA® Pur K 8727/F	100							
RODA® Pur K34/F	30	 	 		<u> </u>		I	1) 3X Spray
RODA® Bind K 4080/N	50				L			Rest Over night
RODA® Feel CLD/N	70				I		I	Iron @ 100℃
RODA® Feel K 980/N	30				I		I	
RODA® Ground KCF 647/N	30						I	2) 3X Spray
RODA® Oil K 4040/N	20				<u> </u>		I	
RODA® Feel Microsil	20				Ī		T	Plain Plate @ 90°C/30 pressure
RODA® KP Pigment Mix	30						I	
IPA	20						I	+3X Spray
WATER	600	500	600				I	
Aquaderm® X Pigment Mix		40	T		I		I	3) 2X Spray
RODA® Base 4095/N		100			L		1	
RODA® Cryl 577/N2		50			I		I	Plain Plate @ 90°C/30 pressure
RODA® Pur EP 19/F		50			Ī		[- T
RODA® Pur WX 1418/F		50	150		<u> </u>		1	
RODA® Bind TLC 327	<u>-</u>	50	 -				1	
RODA® Bind TLC 385		50	150				† !	
RODA® Wax KCF 616	†	50	 -		†		†	
RODA® Wax 4077/N	-	30	30		†		†	
RODA® Feel Microsil		20	30		†		İ	
RODA® Feel F 721		20	30		†		†	
RODA® Link Fix 7			10		†		†	
								
			<u> </u>					
		i	i 		<u> </u>			
		i 	i 				į	
		ļ 	ļ		ļ		ļ	
		i 			ļ		ļ	
		ļ	ļ		ļ		ļ	
		 	ļ		<u> </u>		ļ	
		L	<u> </u>		<u> </u>	L	1	
	I				L		1	
		 			<u> </u>			
			; :		T		Ţ	1 1
 			i		†		1	
	1000	1010	1000	0	0	L	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.