Finishing



CLIENTIILF 24RECIPE NO.IILF 2412ARTICLEFAINTBASED ON WE RECIPE NO.ACI23526WEMATERIALSHEEP FGDATE30 December 2023

COLOUR STRING (TPX 16-1305)

TECHNICIAN

SANKARALINGAM

Product	1	2	3	4	5	6	7	Procedure
RODA® Pur EP 5/N	200	100						1) 1 X Spray
Hypen 93	200							
WATER	600	600	550	950			<u> </u>	2) 3 X Spray
RODA® Base 5514		100						Iron@ 90°C/40k pressure
RODA® Wax KCF 616		100					ļ.	3 X Spray
RODA® Wax KCF 638		100						
RODA® Link 5504		20						3) 2 X Spray
RODA® Lite 07 Mix		100						Iron@ 90°C/50 pressure
RODA® Pur 5427/N			350					
RODA® Fix 6271/B			100					4) 1 X Spray
RODA® Feel S 2075			30					
RODA® Link 5777			20					
AQUADERM® X-Shield HO				50				
AQUADERM® Additive XF				10				
		 		 	 	 	<u> </u>	
	<u>†</u>			:		 !	†	
							 	
	+				<u></u>			
		! 				 		
							 	
		ļ		ļ			 	
	<u>i</u>				<u> </u>		ļ	
							ļ	
		L		i	L	L	İ	
		! L		: !	<u> </u>	L	İ	
	<u>-</u>	 		: :		 	1	
	<u>-</u>	! !		!	!	! !	Ī	
		 !		 !	} !	}	†	
					<u></u>			
								<u> </u>
		ļ					!	<u> </u>
							į	-
		ļ			<u> </u>	ļ	ļ	<u> </u>
							ļ	
						L	İ	
	1000	1120	1050	1010	0		0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.