## Finishing



CLIENT IILF 24 RECIPE NO. IILF2421
ARTICLE HAZEL BASED ON WE RECIPE NO. ACI23517WE

MATERIAL COW FG DATE 19 December 2023
COLOUR WARM SAND (TPX 15-1214) TECHNICIAN SANKARALINGAM

Product	1	2	3	4	5	6	7	Procedure
RODA® Pur ADX	100							1) 2 X Spray
PRIMAL® FGR	100							
RODA® Cryl K 577/N2	100							2) 4 X Spray
Hypen 93	250							Sandblast 90°C/50 pressure
RODA® Cryl 744		50						4 X Spray
RODA® Base 5514		400						
RODA® Pur 64/N		50						3) 3 X Spray
RODA® Lite 07 Mix		100						Sandblast 90°C/50 pressure
EUDERM® Nappa Soft S2		50			T	[	Ĭ	- T
WATER	450	330	350		T	[	Ī	
RODA® Wax W 706	<del>-</del>	50			<del> </del>	 	!	
RODA® Link 5504/N	<u>-</u>	20			Ť	 	İ	
RODA® Fix 5040 Dull			250		Ī		!	
RODA® Pur 5011/N	<u>-</u>		250		İ	! !	!	 
RODA® Feel S 2075			20				!	
RODA® Feel S 5796		i	50		†	i	<del></del>	
RODA® Link C 70			50				i	
RODA® Link 5777		ļ	20		†	<u> </u>	İ	
AQUADERM® Additive XF			30		÷		ļ	
AQUADERIVI Additive XI		}	30		<del></del>	}	<del> </del>	
		<u> </u>			<del></del>	<u> </u>	<del></del>	
		ļ			<del>-</del>	ļ	<del></del>	
					ļ	ļ	ļ	
		ļ			<del></del>	ļ	ļ	
		ļ			<u> </u>	 	ļ	
		ļ			ļ	ļ	ļ	
		i 	 	: 	<u> </u>	! !	i 	
	i	<u> </u>			<u> </u>	<u> </u>	<u> </u>	
	i i	[			1	[		
					1	<u> </u>	:	
						ļ	!	
	<u>-</u>	Ī			Ť	[	Ť	
		ļ			<del>†</del>	i	†	
	<del>-</del>	i			†	i	†	
		ļ			<del></del>		ļ	
	+	ł			<del>†</del>	<del> </del>	<del>†</del>	
	1000	1050	1020		0	L	i	
	1000	1050	1020	0	U		0	

## Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.