## **Finishing**



CLIENT IILF 24 RECIPE NO. IILF 2402
ARTICLE MARL BASED ON WE RECIPE NO. ACI23494WE
MATERIAL SHEEP FG DATE 27 December 2023
COLOUR LIME PUNCH (TPX 13-0550) TECHNICIAN MURUGESAN

Product	1	2	3	4	5	6	7	Procedure
RODA® Pur 5101	100							
RODA® Wax 4097/N	50							1) 5X Spray
RODA® Ground NIC/N	50						ļ.	
RODA® Bind TLC 327	50							2) 2 X Spray
RODA® Feel Microsil	10	10					]	Satilux @90°C
RODA® Feel KTA 950	10	10						Milling - 2hrs
RODA® Lite 07 Mix	30	<u> </u>	† !	!	<u> </u>		!	
RODA® Pur WX 1418/F		100					!	3) 1 X Spray
RODA® Bind TLC 385		100			!			
RODA® Link A 60		5	! !				!	·
WATER	700	775	900				!	!
AQUADERM® Additive XF			10					
RODA® Feel S 2075			20	[	Î	]	1	
RODA® Feel N4			20					
AQUADERM® X-Shield HO	+	ļ	50		†	i	†	
TAGOADERINI A SINCIGITO		ļ		<del></del> -	<del> </del> -		<del></del>	
		ļ		ļ	<del></del>		<del></del>	
		ļ	ļ		ļ	ļ	į	
		ļ	ļ	ļ	<del></del>	ļ	ļ	 
		ļ 	: 	ļ	<u> </u>	ļ	ļ	
		ļ			<u> </u>	ļ	ļ	
		i L	i L	i	i	<u> </u>	İ	
			! !	!	†	¦		
		l	¦	!	†	<u> </u>	†	
		ļ					ļ	
			¦	i	<del></del>		<del></del>	. I
		ļ	¦	<del> </del>	<del> </del> -	<u> </u>	<del></del>	
	-+	ļ	<u> </u>	<del> </del>	<del>-</del>	<u> </u>	<del></del>	
,					ļ		ļ	
		ļ	ļ	ļ	<u> </u>	ļ	ļ	
		ļ 	i 	ļ	<u> </u>		<u> </u>	
	<u> </u>	L	L	l	L	L	1	1
	I	!						
	1		! !	1	1	1	1	
	-†	Ĭ	!	İ	Ť	İ	İ	1
	<del></del>	i		i	<del></del>	i	İ	
	1000	1000	1000	0	0	i	0	+
	1000	1000	1000	U	U		U	<u> </u>

## Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.