Garment								
IENT IILF 24				RECIPE NO.				IILF2410
ARTICLE SPLENDOR				BASED ON WE RECIPE NO.				ACI23514WE
MATERIAL SHEEP FG				DATE				03 January 2024
COLOUR AUTUMN GLOR		TECHNI	CIAN		SANKARALINGAM			
Product	1	2	3	4	5	6	7	Procedure
RODA [®] Base K 5025/FN	50							1) 3 X Spray
RODA® Feel CLD/N	70							Iron@ 80°C/40kg
RODA® Pur K 8727	75							
RODA® Bind K 4080	50							2) 4 X Spray
RODA [®] Ground KCF 647	50							
RODA [®] Wax KCF 638	50	40						3) 2 X Spray
RODA® Feel KTA 950	20							Iron@ 90°C/40kg
AQUADERM® X-Shield HO	40	50	50					
RODA® KP Mix	75							
RODA® Cryl 744		50						
RODA [®] Base AF-B/N		100						
RODA® Pur EP 8		75						
RODA [®] Wax MONO		50						
RODA [®] Cryl NP 86		50						
RODA [®] Lite 07 Mix		100						· • • • • • • • • • • • • • • • • • • •
AQUADERM [®] Additive XF		10	20				 	
WATER	600	550	500		L 		L	. <u>1</u> 1 1
RODA® Fix 6271/B			250					
RODA® Fix 5188/N Gloss	<u> </u>		250					1
RODA® Link C 70			20					
			20					1
	<u>-</u>							
	<u>i</u>							. i

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.