



Tanning

FOC Tanning

ARTICLE	Shoe Upper & Leather Goods	CLIENT	IILF 2024 - ALBINO
MATERIAL	SHEEP PICKLED PELT - INDIAN	RECIPE NO.	ACI23494BH
QUANTITY	10 Skins	DATE	06 December 2023
% based on	fleshed weight	VESSEL	trial drum
weight:	5 kg	TECHNICIAN	ACI TEAM

Process	%	kg	Product	Run	Stop	Comments
	60	3	Water,35 °C			
	6	0,3	Salt	10'		Bé 6.5-7.0
DE-PICKLING	1,5	0,075	Sodium formate	2*10'+30'		
	0,75	0,0375	Sodium bicarbonate	3*10'+45'		Check ph: 4.8-5.0
DEGREASING	0,5	0,025	OROPON® DVP			
	0,5	0,025	PELTEC® AD-N			
	0,5	0,025	BORRON® SE	90'		Check for proper degreasing
Drain	200	10	Water,35 °C	10'		
Drain	60	3	Water,35 °C			
	6	0,3	Salt	10'		Bé 6.5-7.0
	0,5	0,025	MAGNOPAL® IPF	20'		
	0,5	0,025	Formic acid	2*10'+10'		
	0,5	0,025	PRODUCT® F 4142	30'		
	0,5	0,025	Formic acid	2*10'+30'		Check ph: 2.8-3.0 in BCG to Yellow
TANNING	4	0,2	SELLATAN® G50-I	180'		Automatic over night next day run for 10'
	0,5	0,025	Sodium acetate	30'		
	10	0,5	TANIGAN® MB-O LIQ			
	1	0,05	PRODUCT® F 4142	90'		
BASIFICATION	0,5	0,025	SELLASOL® PAK-I	2*10'+45'		Check ph: 4.0-4.2
Drain	200	10	Water,35 °C	10'		
Drain	200	10	Water,35 °C			
	0,1	0,005	BORRON® ST			
	0,1	0,005	Preservative	20'		
Drain						
						Keep ageing for 2 -3 days and check for any area shrinkage,do samm and wet buffing if needed for further processing..

Comments:

ARACIT®, BORRON®, CORIPOL®, CROMENO®, DERMASCAL®, ERHA®, ERHAVIT®, MAGNOPAL®, OROPON®, PELLVIT®, SELLASOL®, SELLATAN® and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.