

Wet-End Gloves

ARTICLE	ALBINO (FOM SHEEP GLOVE CRUSTING - BPS/F)		CLIENT
MATERIAL	PRE-TANNED SHEEP SKIN - INDIAN		RECIPE NO.
QUANTITY	10 skins		DATE
% based on weight:	shaved weight	substance Full suba mm	COLOUR
	5 kg		TECHNICIAN

Process	%	kg	Product	Time
WETBACK	200		water,30°C	
	0,5		PRODUCT® F 4142	
	0,2		PELTEC® AD-N	30'
	1		SELLATAN® G50-I	45'
Drain				
Drain	200		water,30°C	10'
NEUTRALISATION	100		water,30°C	
	2		SELLASOL® PAK-I	
	0,5		Sodium bicarbonate	30'
	3		LEUKOTAN® 1084	
	2		CORIPOL® SLG-I	30'
RETANNING	5		TANIGAN® MB-O LIQ	
	4		TANIGAN® LF-O LIQ	
	2		TANIGAN® DS-O LIQ	
	2		GS POWDER	
	2		RETINGAN® R7-IN	45'
	2		BAYKANOL® PFM	20'
FATLIQUORING	100		water,50°C	
	4		CORIPOL® SLG-I	
	2		CORIPOL® Pure XS	
	4		LEVOTAN® LB	
	3		CORIPOL® DX-1202	
	1		PRODUCT® F 4142	
	0,5		BORRON® SAF	
0,1		Preservative	60'	
FIXING	3		Formic acid	3*10'+40'
Drain				
Drain	200		water,30°C	10'
Drain				

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAI
by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from
supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore com
We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.



IILF 2024
ACI23494WE
11 December 2023
NATURAL
ACI TEAM

Comments

Check for proper wetback

Check ph: 4.8-5.0 in BCG to Deep blue

Check ph: 3.8-4.0
Check for bath exhaustion

**Cool Horse Pile O/N. Next day do light
Samm/Hook to dry /Mollisa for required
softness / Then Shaving at 0.4 -0.5 mm**

N[®], and TANNESCO[®] are registered or filed trademarks, owned

n performing his own tests to determine the suitability of the
es within the customer's sphere of responsibility.