

Wet-End Gloves

ARTICLE	MARL (FOM SHEEP GLOVE - BPS/F)		CLIENT
MATERIAL	FOM SHEEP GLOVE CRUST - INDIAN		RECIPE NO.
QUANTITY	10 skins		DATE
% based on weight:	dry weight	substance 0.4-0.5 mm	COLOUR
	2 kg		TECHNICIAN

Process	%	kg	Product	Time
WETBACK	500	10	water,30°C	
	2	0,04	SELLATAN® G50-I	
	2	0,04	CORIPOL® DX-1202	90'
Drain				
Drain	200	4	water,30°C	10'
NEUTRALISATION	100	2	water,30°C	
	2	0,04	SELLASOL® PAK-I	30'
RETANNING	3	0,06	TANIGAN® MB-O LIQ	
	2	0,04	TANIGAN® LF-O LIQ	20'
DYEING	2	0,04	INVADERM® LU	
	2	0,04	SELLA® FAST YELLOW A	
	0,05	0,001	SELLA® FAST GREEN 2GB	
	1	0,02	MAGNOPAL® HS	45'
FATLIQUORING	200	4	water,50°C	
	4	0,08	CORIPOL® SLG-I	
	4	0,08	CORIPOL® ESU-I	
	3	0,06	CORIPOL® Pure XS	
	4	0,08	LEVOTAN® LB	
	2	0,04	CORIPOL® SG	
	1	0,02	PRODUCT® F 4142	
	0,3	0,006	BORRON® SAF	20'+ 60'
	0,1	0,002	Preservative	
FIXING	3	0,06	Formic acid	3*10'+45'
Drain				
Drain	200	4	water,30°C	10'
TOP FATLIQUORING	200	4	water,50°C	
	3	0,06	CORIPOL® ESU-I	
	3	0,06	CORIPOL® SLG-I	
	2	0,04	CORIPOL® Pure XS	
	2	0,04	LEVOTAN® WS	
	1	0,02	PRODUCT® F 4142	45'
FIXING	2	0,04	Formic acid	10'+30'
Drain				
Drain	200	4	water,30°C	10'

BPS/F OPTIMIZED < 100 ppm

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAI
by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from
supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore com
We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.



IILF 2024
ACI23494WE
15 December 2023
LIME PUNCH (TPX 13-0550)
ACI TEAM

Comments

Check for proper wetback

Check for dye penetration

**Check ph:3.8-4.0
Check for bath exhaustion**

**Check ph:3.8-4.0
Check for bath exhaustion**

**Cool Horse Pile O/N, Next day do Samm/
Hook to dry/ Staking,/ Then Milling for
2 hrs**

N[®], and TANNESCO[®] are registered or filed trademarks, owned

n performing his own tests to determine the suitability of the
es within the customer's sphere of responsibility.