



# Wet-End Shoe Upper

RECIPE NO.

ACI23495WE

CONTINUED

Process	%	kg	Product	Time	Comments
TOP RETANNING	200		water,30°C		
	5		GS Powder		
	5		TANIGAN® F	30'	
	2		LEVOTAN® L	30'	
FIXING	1		Formic acid	10'+20'	Check ph:3.8-4.0 Check for bath exhaustion
Drain					
	200		water,30°C	10'	
Drain					
					Cool Horse Pile O/N. Next day do Samm/ Sett/ hook to dry / Mollisa for required softness

**BIO INDEX - 61 %**

## Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.