## Wet-End

## **Shoe Upper**

ARTICLE	TROPICAL (FOM SHEEP UPPER - BIO)	CLIENT
MATERIAL	PRE-TANNED SHEEP SKINS - INDIAN	RECIPE NO.
QUANTITY	19 skins	DATE
% based on	shaved weight substance <b>0.9-1.0</b> mm	COLOUR
weight:	<b>10</b> kg	TECHNICIAN

weight.	10 KB			TECHNICH (IV
Process	%	kg	Product	Time
	200		water,30°C	
	0,5		PELTEC® AD-N	30'
WETBACK	0,5		Sodium sulphite	30'
WEIDACK	0,5		BORRON® SE	40'
Drain	0,5		DONNON SE	40
	200		water,30°C	10'
Drain				
	100		water,30°C	
BLEACHING	1,5		Oxalic acid	15'
	2		TANIGAN® BL	40'
Drain				
	200		water,30°C	10'
Drain	100		. 2000	
NEUTRALISATION	100		water,30°C	401
	2,5		SELLASOL® NG LIQ	40'
	4		LELIZOTAN® 1004	
	4 1		LEUKOTAN® 1084 CORIPOL® PURE V	40'
	1		CORIPOL <sup>3</sup> PORE V	40
	6		SELLATAN® TMC	
RETANNING	6		RETINGAN® PURE RS	
	5		GS Powder	
	4		TANIGAN® F	
	1		SELLASOL® PURE D	90'
DYEING	0,5		SELLA® STAR DESERT	
	0,3		SELLA® FAST GREY A	
	0,1		SELLA® FAST BROWN A	
	1		SELLASOL® PURE D	45'
	3		SELLASOL® PURE M	30'
	100		water EO°C	
	4		water,50°C <b>LEVOTAN® L</b>	
FATLIQUORING	3		CORIPOL® PURE V	
. ALEQUOMING	2		CORIPOL® SLG-I	
	2		CORIPOL® ICL	
	0,5		PRODUCT® F 4142	60'
	3		SELLASOL® PURE H Liq	30'
FIXING	2		Formic acid	3*10'+40
Drain				
	200		water,30°C	10'
Drain				

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAI licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer fror supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore com We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.



IILF 2024 ACI23495WE 11 December 2023 WARM SAND (TPX 15-1214)

nments
Check for proper wetback
Check for proper bleaching
Check ph: 4.8-5.0 in BCG to Deep blue
Automatic over night next day run for 10
<b>0</b>
Check for dye penetration
,,,,,
Check ph:3.8-4.0
Check for bath exhuastion

 $N^{\circledast},$  and TANNESCO  $^{\circledast}$  are registered or filed trademarks, owned by or

 $\,$  n performing his own tests to determine the suitability of the  $\,$  ies within the customer's sphere of responsibility.