

Wet-End Garment



RECIPE NO.

ACI23526WE

CONTINUED

Process	%	kg	Product	Time	Comments
FATLIQUORING	150		water,50°C		
	6		LEVOTAN® LB		
	3		LEVOTAN® PS		
	3		LUBRITAN® SPE		
	1		MAGNOPAL® DP	60'	
FIXING	1,5		Formic acid	10'+30'	Check ph: 3.8-4.0 Check for bah exhaustion
	1,5		Formic acid	10'+30'	
Drain					
	200		water,30°C	10'	
Drain					

Cool Horse Pile O/N. Next day do light
Samm/Hook to dry/Staking
Mollisa to required softness

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.