

Wet-End Garment



RECIPE NO.

ACI23513WE

CONTINUED

Process	%	kg	Product	Time	Comments
FIXING	100		water,30°C	5'	
	2,5		Formic acid	60'	
	0,5		Formic acid	30'	Check ph: 3.8-4.0
Drain					Check for bath exhaustion
Drain	200		water,30°C	10'	

**Cool Horse Pile O/N. Next day do light Samm
Sett/Vaccum 120'@ 50° C Hook to dry/Staking
Then Buffing & Snuffing**

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.