

Wet-End Shoe Upper



RECIPE NO.

ACI23555WE

CONTINUED

Process	%	kg	Product	Time	Comments
TOP DYEING	200		water,30°C		
	4		SELLA® FAST YELLOW A		
	1		INVADERM® LU	30'	
TOP FATLIQUORING	2		LEVOTAN® WS		
	2		CORIPOL® UFB/W		
	2		LEVOTAN® L	30'	
FIXING	2		Formic acid	30'	
Drain					
Drain	200		water,30°C		
	1		SELLA® FIX HPF Conc	30'	
Drain					
Drain	200		water,30°C	10'	

Cool Horse Pile O/N. Next day do Samm/
hook to dry / Milling for required
softness

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.