



# Wet-End

## Shoe & Leather Goods

RECIPE NO.

ACI23497WE

CONTINUED

Process	%	kg	Product	Time	Comments
	150		water,50°C		
	3		BAYKANOL® PFM-I	20'	
FATLIQUORING	2		CORIPOL® SLG-I		
	2		CORIPOL® UFB/W		
	2		CORIPOL® DX-1202		
	2		LUBRITAN® SPE		
	2		LEUKOTAN® 1084	45'	
	2		TANIGAN® OS-IN		
	2		SELLATAN® MBS POWDER	30'	
	2		MAGNOPAL® SFT-F	20'	
FIXING	3		Formic acid	3*10'+45'	Check ph: 3.8-4.0 Check for bath exhaustion
Drain					
	200		water,30°C	10'	
Drain					

Cool Horse Pile O/N. Next day do light  
Samm/Sett/ Vaccum 50° C 2' hook to  
dry/ Mollisa for required Softness/  
Buffing & Snuffing

### Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.