

Wet-End Shoe Lining



RECIPE NO.

ACI23517WE

CONTINUED

Process	%	kg	Product	Time	Comments
FATLIQUORING	100		water,50°C		
	3		LUBRITAN® SPE		
	3		CORIPOL® SLG-I		
	1		CORIPOL® AT		
	1		CORIPOL® BZN-I	60'	
FIXING	3		Formic acid	2*10'+45'	Check ph: 3.8-4.0 Check for bath exhaustion
Drain					
Drain	200		water,30°C	10'	
Drain					
Drain	200		water,30°C		
Drain	2		TANNESCO® FC	20'	
Drain					
Drain	200		water,30°C	10'	
Drain					
Drain	200		water,30°C		
Drain	1		SELLA® FIX HPF CONC	30'	
Drain					
Drain	200		water,30°C	10'	
Drain					
					Cool Horse Pile O/N. Next day do light Samm/Vacc @ 1Mins Hook to dry/Staking Mollisa to required softness

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.