

Finishing Leather Goods



CLIENT **TFL**
 ARTICLE **N°1 DANDELION**
 MATERIAL **Half calf**
 COLOUR **TPX 13-0758**

RECIPE NO. **MEMA 23043**
 BASED ON WE RECIPE NO.
 DATE **11 July 2023**
 TECHNICIAN **Maurizio Menichetti**

Product	1	2	3	4	5	6	Procedure
RODA® Cryl 5037/N	100						1) 1X ROLLER 20B - 32 g/sqft
Water	200				50		REST OVER NIGHT - VACUUM
RODA® Penetrator IE 880	100						BUFFING PAPER 400
Euderm®X- Grade MP-2		850					2) 1X ROLLER 21G - 10gr.sqft
Baygen®Compact LV-2		100					SANDBLAST 120°C - 40 atm
RODA®Pure Luster 1430		50					BUFFING PAPER 800
RODA®Link 5777		10	30				
RODA®Lite 07 MIX		15	100				3) 2X ROLLER 30X
BAYGEN® Compact LV 2			500				SANDBLAST 80°C - 40 atm
RODA® Base WH 0303/N			500				+2X ROLLER 30X
RODA® Pure Luster 1505			50				4) TIP by ROLLER "Fiamma" by Colibri
Aquaderm®Fluid H			10			10	
RODA® Lac 1028				1000	250		5) 2X SPRAY
SELLA® Derm M2 Mix				60			6) 2X ROLLER 30X
RODA® Poliperl Gold M					8		
Methoxypropanol					250		
RODA® Pur 5805/N3						900	
RODA® Pur W 5814/N Dull						100	
RODA® Link PAX						10	
RODA® Feel Microsil						10	
Total	400	1025	1190	1060	558	1030	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.