Finishing



CLIENT TFL RECIPE NO. MEMA 23050

ARTICLE N°11 NILE BLUE BASED ON WE RECIPE NO.

MATERIAL Half Calf DATE 19 September 2023
COLOUR TPX 15-5210 TECHNICIAN Maurizio Menichetti

Product	1	2	3	4	5	6	Procedure
RODA® Base AF-B/N	200	100	 	 	<u> </u>	 	1) 2X Topstar R25
RODA® Ground UP-XS	400	80	i		i I	Ť	Ironing 80°C 40 atm
RODA® Wax Mono	100	100		<u> </u>	<u> </u>	†	
RODA® Base 5103	200	200		 	! !	i	2) 3X Spray
RODA® Lite 07 Mix	70	50				Ī	
PRIMAL™ SCL-371	40	80		: :	† !	i	3) 2X Spray
RODA® Visc 5722	25				 		
		<u> </u>	i 	<u> </u>	ļ 	<u> </u>	4) 2X Spray
Methoxypropanol		50	ļ 	<u> </u>	<u> </u>	<u> </u>	Ironing 80°C 40 atm
Water		500	500	500	ļ	ļ	Milling 5h
		ļ	 	ļ	ļ 	ļ	Ironing 80°C 20 atm
RODA® Fix 5090		<u> </u>	300	300	<u> </u>	<u> </u>	
RODA® Fix 6271-B		ļ	200	200	! !	ļ	
RODA® Feel N4		<u> </u>	40	40	ļ	<u> </u>	
AQUADERM® XL 71		L	30	30	<u> </u>	L	
RODA® PoliperI M		<u> </u>	3	<u> </u> 	<u> </u> 	<u> </u> 	
	-	<u> </u>	 	i	i !	<u> </u>	
						Ī	
	 	<u> </u>	i 	<u>i</u>	į 	<u> </u>	
					ļ	<u> </u>	
		<u> </u>					
					† ! !		
		<u> </u>	ļ	<u> </u>	<u> </u>	<u> </u>	
	 	<u> </u> 	i I	<u> </u> 	i I	<u> </u> 	
			 	<u> </u>	¦ !	 	
	<u> </u>	†	ļ	İ	İ	i	.i
		<u> </u>			 	<u> </u>	
		<u> </u>	! ! !	<u> </u> 	<u> </u>	<u> </u>	
		ļ		ļ	ļ	ļ	
Total	1035	1160	1073	1070	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.