



Finishing Shoe Upper

CLIENT TFL
 ARTICLE N°19 YELLOW
 MATERIAL SHEEP SKIN
 COLOUR TPX 15-1046

RECIPE NO.
 BASED ON WE RECIPE NO.
 DATE
 TECHNICIAN

BU 6084
 Sept. 2023
 SANKARALINGAM

Product	1	2	3	4	5	6	7	Procedure
RODA® Ground NIC/N	200							
RODA® Pur K 8727/F	50							
RODA® Pur K 34/F	20							1) 3X SPRAY
RODA® Bind K 4080	50							SANDBLAST @ 90°C/90 Kg
RODA® Wax K 619/N	60			200				
RODA® Feel KTA 950	20			50				2) 3X SPRAY
RODA® Feel CLD-N2	20			50				SANDBLAST @ 90°C/90 Kg
RODA® KP Mix	70							+3X SPRAY
RODA® Feel KTA 944	5	10						
WATER	500	500	620	700				3) 2X SPRAY
RODA® Base AF-B/N		100						
RODA® Cryl NP 87		50						4) 2X SPRAY
RODA® Pur EP 8/F		50						IRON 100°C - 50Kg
RODA® Bind TLC 327		50						
RODA® Bind TLC 385		50						
RODA® Wax MONO		80						
RODA® Penetrator IE 880/N2		30						
RODA® Lite 07 Mix		70						
RODA® Pur 5427/N			150					
AQUADERM® X-BIOMER® FTC			150					
RODA® Fix 6271-B			50					
RODA® Feel N4			10					
AQUADERM® Additive XF			10					
RODA® Link PAX			10					
Total	995	990	1000	1000	0		0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.