Finishing

Shoe Upper

CLIENT	**TFL**	RECIPE NO.	**BU 6081**
ARTICLE	**CREAM**	BASED ON WE RECIPE NO.	
MATERIAL	**LAMB SKIN**	DATE:	**Sept. 2023**
COLOUR	**TPX 15-1046**	TECHNICI	**Tirelli/ Giaquinto**

Product	1	2	3	4	5	6	Procedure
RODA® Base 5698	100						
WATER	300	600	500				1) 2X SPRAY
RODA® Casi MIX	20	90					ROTOPRESS 100°C-50 ATM
RODA® Pure Luster 1505		50					
RODA® Bind 1430		50					2) 8X SPRAY
RODA® Wax KCF 616		50					
RODA® Pur 8103		100					ROTOPRESS 90°C-50 ATM
RODA®Pur WX 1418/F		50					STAKING
RODA®Cryl NP 87		50					ROTOPRESS 90°C-20 ATM
SELLA® Derm M2 MIX		10					
RODA® Link PAX		3	6				
RODA® Lac WG 4			300				
RODA® Pur 5329 Conc.			150				
RODA® Feel N4			5				
RODA® Bind TLC 327			50				
Total	**420**	**1053**	**1011**	**0**	**0**	**0**	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.