Finishing

Leather Goods

CLIENT TFL RECIPE NO. BU 6046

ARTICLE N°4 BAJA BLUE BASED ON WE RECIPE NO.

MATERIAL baby calf corrected grain DATE 12.07.2023 COLOUR 18-3946 TECHNICIAN GIRAUDO

Product	1	2	3	4	5	6	Procedure
RODA® Lite 07 mix		150					1) 1 spray coat, dry , ironing at 80°C / 40 bar
AQUACAST® S	350			T		T	2) 3 reverse coats, (21G)dry, ironing at 80°C / 40 bar
RODA® Pure Luster 1430	170					1	3 reverse coats (tot. Approx 50 gr sq,ft), dry
BAYGEN® Compact DD		750				1	
BAYDERM® Bottom DLV-N		100					
AQUADERM® XL 50		30				1	
AQUADERM® Fluid H		10				T	3)1- 2 spray coats, dry
ISODERM® LO 87			500			1	
Butyl-Acetate			500			1	
**C 261 (1:2 MOP)			5				!
water	480			†		İ	
				ii		İ	
				T		1	4) 1 curtain coat (approx 18 gr sq,ft)
BAYGEN® Top U 01				1000		ļ	dry overnight in a well ventilated room
*Solvent Mixture		!		350-400		1	at a room temperature of 45°C
BAYGEN® Hardener SN 2				680			
				†		İ	
Viscosity (DIN CUP 4 mm)		30-35"		26-28"		İ	
				1		İ	
				†		ļ	
				†		†	
							
				 		ļ	
				i		į	
						-	
		 		 			
				<u> </u>		ļ	
				 		ļ	
				 		į	
				ļi		ļ	
		ļ		ļi		ļ	
				i		ļ	
		ļ		ļ		ļ	
		ļ		ļ		ļ	
		İ		ļ		ļ	
						į	
		i		<u> </u>		į	i
				<u> </u>		ļ	i
		<u> </u>		<u> </u>		<u> </u>	
						1	
						I	
						Ī	
Total	1000	1040	1005	1680	0	0	

Comments: ** product from ECKART

before to finishing: buffed leather 2 x 400 paper, *Solvent Mixture (water free, PU-grade quality)

Buthyl acetate 500 pts.

Ethyl acetate 500 pts.

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.