Finishing

Shoe Upper

CLIENT TFL RECIPE NO. BU 6082

ARTICLE N°5 TANGO BASED ON WE RECIPE NO.

MATERIAL COW SIDE BUFFED GRAIN DATE 18 July 2023
COLOUR TPX 18 - 3946 TECHNICIAN Bruno Parreira

Product	1	2	3	4	5	6	Procedure
LEUKOTAN™ 1093	650						
WATER	300		370				1) 1X ROLLER 40 gr. sqft
ACETIC ACID	50						DRY UNTIL 10%
RODA®Polipearl Micro		300					STAKING MACHINE TO CRACK EFFECT
RODA®Pur 5805/N3		600	500				WET BACK (SEE RECIPE 2ND STAGE)
RODA®Bind TLC 385		100	100				SET OUT/VACUUM
RODA®Feel Microsil			20				AIR DRY, STAKING MACHINE
RODA®Link C 70			10				
							2) 4X ROLLER DESIGN
							3) 3X SPRAY
							PLATE 110°C
	100	1005	1005				
Total	1000	1000	1000	0	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.